

# TECHNICAL DATA SHEET

## **Stannous Octoate T-9**

## **Introduction and Applications**

GD T-9 is a strong metal based urethane (polyol-isocyanate) catalyst that is primarily used in flexible slabstock polyurethane foams. It also can be applied to catalyze polyurethane coating, elastomer, room temperature curing silicone rubber.

#### **Performance**

- Because it is a bivalent tin compound, it remains in foam after foaming and has no adverse effect on the foam properties.
  - GD T-9 is also a anti-aging agent staying in the foam .

## **Specification**

Product	GD T-9
Appearance	Light yellow transparent liquid
Stannous Tin	≥27.8WT%
Total Tin	≥28.8WT%
Vis (at 25°C), mPa·s	<380 mPa.s
Density @25°C	$1.250 \text{ g/cm}^3$

#### **Package**

210 KG in Steel Drum, 25 kg plastic drum

### Shelf Life and Storage

This product has a shelf life of 1 year when stored at recommended temperature  $10\text{-}40\,^{\circ}\text{C}$  and in the original container .

#### Shipping and Handling

This product is not classified in hazardous article in sea way .

When using this product please review the latest Materials Data Sheet and label for product safety information, handling instructions, personal protective ifnecessary.

Qichen Chemical Co., Ltd.

www.gichenchemical.com